



PRODUCT CLASS

Type C

AB03 POLY PRO


3 strands floating line

**AB03
POLY PRO**

CORE : Polypropylene HT

COVER : Absent

ANIMA : POLYPROPYLENE HT



COVER TECH MIX : ASSENTE

FIBER CHARACTERISTICS

The fiber's components of this product are : **POLYPROPYLENE HT**

- **Polypropylene** is a thermoplastic polymer made from the combination of propylene monomers



FIBER'S PROPERTY	UDM	POLYPROPYLENE HT	-	-
Tenacity	gr/den	6,5	-	-
Specific gravity	gr/cm ³	0,910	-	-
Elongation at break	%	20	-	-
Tensile modulus	gr/den	120	-	-
Melting point	°C	164	-	-



COVER ABSENT

BRAID CHARACTERISTICS

CORE		COVER (it's a media of the of all fiber's components)		
Tenacity	6,5 gr/den	Abrasion resistance	-	gr/den
Creep	- %	Peack of temp.	-	°C
Module	120 gr/den	Grip	-	frict. coeff.
Weight	0,910 gr/cm ³	Weight	-	gr/cm ³

DISCOUNT SYSTEM			
SHOP		WHOLESALE	
Standard lenght	sc. %	Standard lenght	sc. %
-	-	-	-
-	-	-	-

APPLICATIONS , TECHNICAL DATA , PRICE

- High vis and floating line for mooring in the bay

--	--	--	--

∅	weight	breacking load	standard lenght	custom lenght	∅	yellow high vis	-	-	-
mm	gr/mt	daN	mt	mt	mm	€/mt	-	-	-
6	16,0	670	200	-	6	0,408 €	-	-	-
8	29,0	1.100	200	-	8	0,672 €	-	-	-
10	45,0	1.700	200	-	10	0,938 €	-	-	-
12	65,0	2.430	200	-	12	1,355 €	-	-	-
14	89,0	3.100	200	-	14	1,856 €	-	-	-
16	116,0	4.120	200	-	16	2,419 €	-	-	-
18	146,0	5.100	200	-	18	3,044 €	-	-	-
20	181,0	6.350	200	-	20	3,774 €	-	-	-
22	219,0	7.650	200	-	22	4,566 €	-	-	-
24	260,0	8.900	200	-	24	5,421 €	-	-	-
26	306,0	10.300	200	-	26	6,380 €	-	-	-
28	354,0	11.800	200	-	28	7,381 €	-	-	-
30	407,0	13.500	200	-	30	8,486 €	-	-	-
32	463,0	15.420	200	-	32	9,654 €	-	-	-
34	-	-	-	-	34	-	-	-	-
36	586,0	19.000	200	-	36	12,218 €	-	-	-
38	-	-	-	-	38	-	-	-	-
40	723,0	22.500	200	-	40	15,075 €	-	-	-

Shock absobtion at 50% of breacking load....13,00%

* Linear breaking load in according to DIN EN ISO 2307