

PRODUCT CLASS

Type A




SK78 UNI SHAKLE

Dyneema core + Dyneema cover

CORE : DYNEEMA SK78 (PRE-STRETCH HPT + PU RESIN TREATMENT)



COVER TECH MIX : DYNEEMA SK78



SK78 UNI SHAKLE

- CORE :** Dyneema SK78 pre-stretch + poliurethane resin treatment
- COVER :** **Tech mix** Absent

FIBER'S CHARACTERISTICS

The fiber's components of this product are : **DYNEEMA SK78**

- **Dyneema** it's an ultra high molecular weight polyethylene .



FIBER'S PROPERTY	UDM	DYNEEMA SK78	-	-	-
Tenacity	gr/den	39,8	-	-	-
Specific gravity	gr/cm ³	0,974	-	-	-
Elongation at break	%	3,5	-	-	-
Tensile modulus	gr/den	1.314	-	-	-
Melting point	°C	147	-	-	-

BRAID CHARACTERISTICS

CORE			COVER (it's a media of the of all fiber's components)		
Tenacity	39,8 gr/den	Abrasion resistance	39,8 gr/den		
Creep	0,5 %	Peack of temp.	147 °C		
Module	1.314 gr/den	Grip	0,06 frict. coeff.		
Weight	0,974 gr/cm ³	Weight	0,947 gr/cm ³		

DISCOUNT SYSTEM					
SHOP			WHOLESALE		
Custom lenght	sc.	%	Custom lenght	sc.	%
Standard lenght	sc.	%	Standard lenght	sc.	%
-	-	-	-	-	-

APPLICATIONS , TECHNICAL DATA , PRICE

- Extreme performane textyle soft shakle

red	royal			
green	yellow			
black	grey			

Ø	weight	working load	breacking load	measure	custom lenght	Ø	solid colors	-	-	-
mm	gr/mt	daN	daN	cm	mt	mm	€/pz	-	-	-
7F 6 ^{1/32}	13,7	1.500	4.500	13	on request	6	35,0 €	-	-	-
10F 8 ^{2/32}	24,7	2.500	7.500	15	on request	8	40,0 €	-	-	-
16F 10 ^{2/32}	44,6	4.000	12.000	17	on request	10	45,0 €	-	-	-
21F 12 ^{3/32}	63,0	5.500	16.500	18	on request	12	50,0 €	-	-	-
-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-	-

Stretch at 30% of breacking load....2,15%
Stretch at breacking load.....3,50%

* Linear breaking load in according to DIN EN ISO 2307